



# TECHNICAL DATA

## #202 Modified Emulsion

### Acrylic Latex Modified Asphalt Emulsion

#### DESCRIPTION

#202 Modified Emulsion is a single component, clay stabilized asphalt-based emulsion, modified with acrylic latex to yield a permanently elastomeric waterproofing compound for cold process built-up roofing. #202 Modified Emulsion meets or exceeds the requirements of ASTM D 1227 Type III and Federal Specification SS-R-1781 Type III.

*Each roof application has unique requirements and as such may require a specific system configuration and application. This product is manufactured to our product specification and our only obligation shall be to replace such product if proven to be defective. Thermo Manufacturing Systems, LLC does not assume responsibility for any defects in application of this product, or any deficiencies in any roof or substrates on which this product is applied, nor shall Thermo Manufacturing Systems, LLC be responsible or liable for injury, loss, or damage of any kind or character, direct or consequential, arising from the application, use or inability to use this product.*

#### USES

#202 Modified Emulsion is designed for use in conjunction with specific polyester reinforcing ply felts to form an integral component of numerous UL classified roofing assemblies as well as an excellent below grade damp-proofing material. #202 SEBS Modified Emulsion is very useful as a primer. #202 SEBS Modified Emulsion is also used as a surface coat to embed gravel and granules over BUR and modified bitumen systems.

#### COLOR

Brown when wet and cures black.

#### STORAGE STABILITY

One year when stored in unopened containers at 40°F - 80°F. DO NOT FREEZE.

#### CLEAN UP

Water

#### PRIMER

On properly prepared surfaces, no priming is needed for application to plywood, most metal, BUR or modified bitumen.

#### CURE TIMES

When applied at 22 wet mils coating thickness and at conditions of 75°F and 50% relative humidity, #202 Modified Emulsion should reach final cure in 24 hours. Colder weather and/or higher humidity will tend to retard curing whereas warmer weather and/or lower humidity will tend to accelerate curing.

#### LIMITATIONS

#202 Modified Emulsion will freeze and should not be shipped or stored at temperatures below 32°F. #202 Modified Emulsion is not recommended for installations where ponding water is likely to occur for longer than 48 hours. #202 Modified Emulsion should not be applied when weather conditions will not permit drying, i.e. high relative humidity (>90%), just before rain, dew, freezing temperatures or sunset.

#### PACKAGING

Available in 5 gallon pails, 55 gallon drums and totes

#### SURFACE PREPARATION

#202 Modified Emulsion is supplied ready to use. Thinning is not required or recommended. If required, stir the materials slowly to ensure uniformity. DO NOT MIX AT HIGH SPEED. All surfaces to be coated must be clean, dry and free of any oil, grease or dirt.

## APPLICATION INSTRUCTIONS

Apply by brush, roller with long nap, or conventional or airless spray equipment

## WARRANTY

When installed by an approved applicator and with an approved maintenance program, various extended warranties are available for specific Thermo Materials® Roof Restoration Systems by notifying Thermo Manufacturing Systems, LLC **PRIOR** to job start. Call for details regarding warranty application documentation requirements.

## APPROVALS



## TYPICAL PHYSICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD
Weight per Gallon	8.5 lbs ± 0.5 lbs	
Solids Content by Weight	50% ± 5%	
Viscosity (KU)	> 140	
Viscosity (cPs)	> 15,000	
Elongation (unreinforced) % min. @ 73°F	625	ASTM D 412
Tensile Strength (unreinforced) nominal psi @ 73°F	150	ASTM D 412

©2014 Thermo Manufacturing Systems, LLC

P.O. Box 218

Lindale, TX 75771

(800) 882-7007

(903) 881-8771

FAX (903) 881-8787

The information contained herein is believed to be reliable. All recommendations or suggestions are made without guarantee in as much as conditions and methods of commercial use are beyond our control. Properties given are typical values and are not specifications unless otherwise stated.