



TECHNICAL DATA

Thermopolyester SB-075

2.75 oz. Soft Stitchbonded Polyester

DESCRIPTION

Thermopolyester SB-075 is a stitchbonded polyester for use as reinforcement in cold process roofing systems. Thermopolyester SB-075 is used as an integral component in numerous UL classified roofing assemblies.

Each roof application has unique requirements and as such may require a specific system configuration and application. This product is manufactured to our product specification and our only obligation shall be to replace such product if proven to be defective. Thermo Manufacturing Systems, LLC does not assume responsibility for any defects in application of this product, or any deficiencies in any roof or substrates on which this product is applied, nor shall Thermo Manufacturing Systems, LLC be responsible or liable for injury, loss, or damage of any kind or character, direct or consequential, arising from the application, use or inability to use this product.

USES

Thermopolyester SB-075 is very soft, providing excellent conformability and elongation for irregular surfaces, such as filled gravel, asphalt shingles and corrugated metal.

COLOR

White

STORAGE STABILITY

Store off the ground on pallets or dunnage with complete protection against weather until installed.

PACKAGING

Roll size 20" x 324'
 12" x 250'
 6" x 250'
 4" x 250'

WARRANTY

When installed by an approved applicator and with an approved maintenance program, various extended warranties are available for specific Thermo Materials® Roof Restoration Systems by notifying Thermo Manufacturing Systems, LLC **PRIOR** to job start. Call for details regarding warranty application documentation requirements.

©2014 Thermo Manufacturing Systems, LLC

P.O. Box 218

Lindale, TX 75771

(800) 882-7007

(903) 881-8771

FAX (903) 881-8787

The information contained herein is believed to be reliable. All recommendations or suggestions are made without guarantee in as much as conditions and methods of commercial use are beyond our control. Properties given are typical values and are not specifications unless otherwise stated.