



# TECHNICAL DATA

## Thermolene<sup>®</sup> SEBS Stainblocker

### Stain Blocking Aluminum Base Fluid-Applied Membrane

#### DESCRIPTION

Thermolene<sup>®</sup> SEBS Stainblocker (styrene ethylbutylene styrene) is an elastomeric single component block co-polymer fluid-applied membrane designed with stain blocking properties. Thermolene<sup>®</sup> SEBS Stainblocker is VOC compliant.

*Each roof application has unique requirements and as such may require a specific system configuration and application. This product is manufactured to our product specification and our only obligation shall be to replace such product if proven to be defective. Thermo Manufacturing Systems, LLC does not assume responsibility for any defects in application of this product, or any deficiencies in any roof or substrates on which this product is applied, nor shall Thermo Manufacturing Systems, LLC be responsible or liable for injury, loss, or damage of any kind or character, direct or consequential, arising from the application, use or inability to use this product.*

#### USES

Thermolene<sup>®</sup> SEBS Stainblocker is formulated with special stain blockers to prevent asphaltic bleed through of residue on metal roofs, aged modified bitumen and aged BUR. Product should be applied when substrate temperature is more than 40°F and less than 100°F. Thermolene<sup>®</sup> SEBS Stainblocker base coat must be covered with Thermolene<sup>®</sup> SEBS Reflective surface coat.

#### COLOR

Aluminum

#### STORAGE STABILITY

Twenty four months when stored in unopened containers at 40°F - 80°F. DO NOT FREEZE.

#### CLEAN UP

Mineral Spirits

#### PRIMER

On properly prepared surfaces, no priming is needed for application to most metal, BUR and modified bitumen.

#### CURE TIME

When applied at 16 wet mils coating thickness and at conditions of 75°F and 50% relative humidity, Thermolene<sup>®</sup> SEBS Stainblocker will dry to the touch in 2 hours, but should not be recoated until it has reached full cure usually within 24 - 48 hours. Colder weather and/or higher humidity will tend to retard curing whereas warmer weather and/or lower humidity will tend to accelerate curing.

#### LIMITATIONS

Thermolene<sup>®</sup> SEBS Stainblocker should not be shipped or stored at temperatures below 32°F. Thermolene<sup>®</sup> SEBS Stainblocker is not recommended for installations where ponding water is likely to occur for longer than 48 hours. Thermolene<sup>®</sup> SEBS Stainblocker should not be applied when weather conditions will not permit drying, i.e. high relative humidity (>90%), just before rain, dew, freezing temperatures or sunset. Keep product away from heat, sparks and open flame.

#### PACKAGING

Available in 5 gallon pails or 55 gallon drums

#### SURFACE PREPARATION

Thermolene<sup>®</sup> SEBS Stainblocker is supplied ready to use. Thinning is not required or recommended. If required, stir the materials slowly to ensure uniformity. DO NOT MIX AT HIGH SPEED. All surfaces to be coated must be clean,

dry and free of any oil, grease, dirt or rust. Rust must be removed and area treated with appropriate Thermo Materials® products.

### APPLICATION INSTRUCTIONS

Apply by brush, roller with long nap, or conventional or airless spray equipment

### WARRANTY

When installed by an approved applicator and with an approved maintenance program, various extended warranties are available for specific Thermo Materials® Roof Restoration Systems by notifying Thermo Manufacturing Systems, LLC **PRIOR** to job start. Call for details regarding warranty application documentation requirements.

### TYPICAL PHYSICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD
Weight per Gallon	8.5 lbs ± .5 lbs	
Solids Content by Weight	65% ± 2%	
Viscosity (KU)	85 – 95	
Viscosity (cPs)	> 140	
Initial Elongation	400%	ASTM D412
Initial Tensile Strength	800 psi	ASTM D412
Low Temperature Flex after 1000 hrs Xenon Arc Aging	Pass	
Fungi Resistance	Zero Rating	

©2014 Thermo Manufacturing Systems, LLC

P.O. Box 218

Lindale, TX 75771

(800) 882-7007

(903) 881-8771

FAX (903) 881-8787

The information contained herein is believed to be reliable. All recommendations or suggestions are made without guarantee in as much as conditions and methods of commercial use are beyond our control. Properties given are typical values and are not specifications unless otherwise stated.