

3. Cold Adhesive – [Thermoflex T-CAP Adhesive](#)
4. Cold Flashing Adhesive – [Thermoflex SBS Adhesive Trowel Grade](#)
5. Base Sheet – [Thermoflex 7025](#) (1.5 sq SBS Polyester Base Sheet)
6. Interply Sheet – [Thermoflex 7225](#) (1 sq SBS Polyester Smooth Surfaced Cap Sheet)
7. Cap Sheet – [Thermoflex 7226](#) (1 sq SBS Polyester Mineral Surfaced Cap Sheet)
8. Flashing Base – [Thermoflex 7025](#) (1.5 sq SBS Polyester Base Sheet)
9. Flashing Cap – [Thermoflex 7226](#) (1 sq SBS Polyester Mineral Surfaced Cap Sheet)

RECOMMENDED THERMO SYSTEM

1. Remove the existing roof down to the deck and clean as necessary. Deck surface is to be made free of latent moisture or loose debris by brooming or other means.
2. Attach insulation and densdeck per local project requirements.
3. Install a single ply of [Thermoflex 7025](#) Base Sheet using a 2-gal/sq application of [Thermoflex T-Cap Adhesive](#) Cold Adhesive. [Thermoflex T-Cap Adhesive](#) Cold Adhesive should be applied to the surface with a notched squeegee or sprayer and allowed to flash for several minutes prior to installing base membrane. Offset each row of [Thermoflex 7025](#) Base Sheet a minimum of 12" to the previous row with end laps having a 6" minimum overlap and edges a 2" minimum overlap.
4. Install a single ply of [Thermoflex 7225](#) Interply Sheet using a 2-gal/sq application of [Thermoflex T-Cap Adhesive](#) Cold Adhesive. [Thermoflex T-Cap Adhesive](#) Cold Adhesive should be applied to the surface with a notched squeegee or sprayer and allowed to flash for several minutes prior to installing interply membrane. Offset each row of [Thermoflex 7225](#) Interply Sheet a minimum of 12" to the previous row with end laps having a 6" minimum overlap and edges a 2" minimum overlap.
5. Install a single ply of [Thermoflex 7226](#) Cap Sheet using a 2-gal/sq application of [Thermoflex T-Cap Adhesive](#) Cold Adhesive. [Thermoflex T-Cap Adhesive](#) Cold Adhesive should be applied to the surface with a notched squeegee or sprayer and allowed to flash for several minutes prior to installing cap sheet membrane. Offset each row of [Thermoflex 7226](#) Cap Sheet a minimum of 12" to the previous row with end laps having a 6" minimum overlap and edges a 3" minimum overlap.
6. Flashing assemblies shall consist of a [Thermoflex 7025](#) Flashing Base and a [Thermoflex 7226](#) Flashing Cap and be fully adhered in a 2-gal/sq application of [Thermoflex SBS Adhesive Trowel Grade](#) Cold Flashing Adhesive.